CITGO® Overdrive HD® Grease



OVERVIEW



- Designed for extended-service applications.
- Especially suited for applications where outstanding protection is required.
- Provides superior performance to stay put and protect under a wide variety of conditions.

FEATURES & BENEFITS



- Outstanding corrosion protection even in conditions where salt water is present.
- Extreme pressure (EP) and anti-wear protection in applications where high loads and metal-to-metal friction exist.
- Polymer-fortified to provide improved adhesion.
- Outstanding stability resists softening even in conditions where water is present.
- Formulated with a proprietary lithium complex thickener that is compatible with many other greases on the market.

APPLICATIONS



- Recommended for use in fifth wheels, spring pins, chassis lubrication, king pins, and universal joints.
- Especially suitable for applications where extreme stability, water resistance, corrosion resistance, wear protection, and EP protection are required.
- Provides excellent performance in many off-road construction and mining applications.
- Not recommended for disc brake wheel bearings.
- Refer to equipment owner's manual for proper lubricant recommendation.

CITGO LUBRICANTS

CITGO Overdrive HD Grease

PROPERTIES



Typical Properties for CITGO Overdrive HD Grease:

Material Code	655377001
NLGI Grade	2
Thickener Type	Lithium Complex
Color	Green
Texture	Smooth, Adhesive
Worked Penetration, ASTM D217	265-295
Dropping Point, ASTM D566, °F(°C)	430 (221)
Rust Prevention, ASTM D1743	Pass
Emcor Corrosion Protection, ASTM D6138, Rating	Pass
5% Synthetic Salt Water Corrosion, ASTM D5969, Rating	Pass
Water Washout, ASTM D1264, % Loss @ 175°F	1.4
Water Spray Off, ASTM D4049, % loss	15.1
Four-Ball Wear, ASTM D2266, mm	0.4
Four-Ball Weld, ASTM D2596, kgf	500
Timken OK Load, ASTM D2509, lbs	65
US Steel Mobility @ 0°F, gpm	12.5
Base Oil Viscosity @ 40°C, cSt	540

CITGO is a registered trademark of CITGO Petroleum Corporation. All other registered trademarks or trademarks are the property of their respective owners. Values shown are typical values only and do not constitute a specification. The information contained herein is subject to change without notice.