CITGO® A/W Hydraulic Oils



	 Superior anti-wear hydraulic and circulating fluids designed for service in high-pressure, high-output industrial hydraulic circuits and specially formulated with thermally stable additives. Outstanding chemical stability, resistance to sludge formation, and anti-wear protection.
FEATURES & BENEFITS	 Thermally stable zinc-based additives protect against heat-related sludge formation in sensitive electro-hydraulic servo valves. Ideal for high-output equipment where sustained heat is prevalent, such as CNC machine tools. Inhibited against rust in both fresh and sea water, and pass Procedures A and B of the ASTM D665 Rust Test. Resist foaming and will not foster abnormal air entrainment in properly designed hydraulic circuits. Readily separate water, allowing water contamination to be drained from the sump.
APPLICATIONS	 Recommended for service in vane, piston, and gear pumps when used in accordance with equipment manufacturers' recommendations. Designed to provide excellent service life to pumps and circuit components such as motors and servos. Recommended for use as a gear and bearing lubricant in industrial applications where rust- and oxidation-inhibited oils are required. Approved against the stringent performance requirements of: Eaton E-FDGN-TB002-E Fives Cincinnati P-68, P-69, and P-70 Parker Denison HF-0 AFNOR NF E 48-603 HM

CITGO Petroleum Corporation Houston, Texas Customer Service Line 1-800-331-4068 LubesCS@CITGO.com Product Answer Line 1-800-248-4684 lubeshelp@CITGO.com

Online at www.CITGOLubes.com

C 10029

PROPERTIES



Typical Properties for CITGO A/W Hydraulic Oils:

Grade	32	46	68
Material Code	633491001	633492001	633493001
Gravity, ASTM D4052, °API	32.6	31.2	30.8
Density, lb/gal	7.18	7.24	7.26
Flash Point, COC, ASTM D92, °F (°C)	417 (214)	446 (230)	468 (242)
Viscosity ASTM D445			
cSt at 40°C	32.3	46.6	68
cSt at 100°C	5.59	6.96	9.0
Viscosity Index	111	106	107
Pour Point, ASTM D97, °F (°C)	-27 (-33)	-22 (-30)	-17 (-27)
Color, ASTM D1500	L0.5	L0.5	L0.5
Water Separability at 54°C, ASTM D1401	40-40-0	40-40-0	40-40-0
Oxidation Test, ASTM D943, Hrs.	5000	5000	5000
Rust Test, ASTM D665 A, B	Pass	Pass	Pass
Eaton E-FDGN-TB002-E	Yes	Yes	Yes
Meets Parker Denison HF-0 Requirement	Yes	Yes	Yes
Meets Fives Cincinnati Requirement	P-68	P-70	P-69
AFNOR NF E 48-603	HM32	HM46	HM68

CITGO is a registered trademark of CITGO Petroleum Corporation. All other registered trademarks or trademarks are the property of their respective owners. Values shown are typical values only and do not constitute a specification. The information contained herein is subject to change without notice.

CITGO Petroleum Corporation Houston, Texas Customer Service Line 1-800-331-4068 LubesCS@CITGO.com Product Answer Line 1-800-248-4684 lubeshelp@CITGO.com

Online at www.CITGOLubes.com

Manufactured in USA