

CITGO EP COMPOUNDS



Date 04/18

DESCRIPTION: CITGO EP Compounds are designed for industrial gear lubrication extra-duty service in a wide variety of applications where extreme pressure load conditions prevail.

BENEFITS: CITGO EP Compounds are formulated with highly refined base stocks and select ashless additives to assure premium extreme pressure properties and provide effective lubrication under most service conditions.

These products can be used in mist lubrication systems and allow directed delivery of the oil and control of stray mist.

CITGO EP Compounds have a high viscosity index, excellent demulsibility, solution stability and thermal stability properties. They also provide excellent resistance to oxidation and foaming and are noncorrosive.

APPLICATIONS: CITGO EP Compounds have been formulated to meet recognized industrial gear oil requirements including:

DIN 51517 Part 3 CLP

US Steel 224

AGMA 9005-E02

ISO 12925-1 CKC/CKD

David Brown S1.53.101 (E)

GM LS2 EP Gear Oil

Fives Group Machine Gear Oil

They are recommended for lubrication of plain and antifriction bearings and gear drives that operate under extra-heavy-duty conditions.

These lubricants can be applied via misting systems and are suitable for use in bearing oil circulating systems.

Typical applications are steel mills, rubber mills, and similar heavy industries where ambient conditions include water, dirt, and scale.

CITGO EP Compounds are formulated for the lubrication of industrial spiral bevel, helical, spur and herringbone gears. They are especially well-suited for use in multiple gear drives that operate at greatly increased pressure between the surfaces of the gear teeth or where severe shock or heavy loads are encountered.

NOTE: Consult your owner's manual for proper lubricant selection.

CITGO is a registered trademark of CITGO Petroleum Corporation. All other registered trademarks or trademarks are the property of their respective owners.

(Continued)

CITGO EP COMPOUNDS



Date 04/18 - (Continued)

		CITGO EP COMPOUNDS							
Grade		68	100	150	220	320	460	680	800
Material Code		631110001	631120001	631130001	631140001	631150001	631170001	631180001	631181001
Gravity, ASTM D4052, °API		30.6	30.2	28.0	27.5	27.0	26.3	26.8	24.0
Density, lb/gal at 60°F		7.27	7.29	7.39	7.41	7.43	7.47	7.49	7.6
Flash Point, COC, ASTM D92, °F (°C)		464 (240)	482 (250)	509 (265)	491 (255)	500 (260)	491 (255)	572 (300)	482 (250)
Viscosity:									
ASTM D445, cSt at 40°C		67.5	97	147.5	215	314	435	639	805
cSt at 100°C		8.6	11.0	14.5	18.5	23.9	30.6	35.8	43.6
Viscosity Index, ASTM D2270		99	97	95	94	96	96	90	95
Pour Point, ASTM D97, °F(°C)		5 (-15)	5 (-15)	5 (-15)	5 (-15)	5 (-15)	5 (-15)	15 (-9)	15 (-9)
Color, ASTM D1500		1.0	2.5	3.0	3.0	3.5	4.0	D8.0	4.5
Copper (Cu) Corrosion, ASTM D130 ⁽¹⁾		1 B	1 B	1 A	1 B	1 A	1 A	2 C	2 C
Demulsibility, ASTM D2711B									
Water in Oil, %		1.0	1.0	1.0	1.0	1.0	1.0	2.0	2.0
Total Free Water, mL		80	80	80	80	80	80	80	80
Emulsion, mL		1.0	1.0	1.0	1.0	1.0	2.0	2.0	2.0
Oxidation Test ⁽²⁾		Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass
Rust Test, ASTM D665A & B		Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass
Timken OK Load,									
ASTM D2782, lbs.		65	70	85	65	70	75	70	70
Four Ball EP Test, Weld,									
ASTM D2783, kg		315	315	315	315	315	315	315	315
Four Ball Wear at 20 kg,									
ASTM D4172, mm		0.29	0.30	0.29	0.23	0.21	0.20	0.35	0.35
Foam Test, ASTM D892,									
Seq. I, II, III		Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass
ISO VG No.		68	100	150	220	320	460	680	Between 680-1000
AGMA Grade		2 EP	3 EP	4 EP	5 EP	6 EP	7 EP	8 EP	Between 8 & 8A EP
Fives Cincinnati		P-63	P-76	P-77	P-74	P-59	P-35	-	-
U.S. Steel Req. No. 224		Meets	Meets	Meets	Meets	Meets	Meets	-	-

Notes: (1) Three hours at 212°F.

(2) Per U.S. Steel Requirement No. 224 (ASTM D2893, 312 hrs. at 99°C).

CITGO is a registered trademark of CITGO Petroleum Corporation. All other registered trademarks or trademarks are the property of their respective owners.