



CITGO CALSUPLEX MP GREASE

Date 04/18

**DESCRIPTION:** CITGO Calsuplex MP Grease is specially formulated with a calcium sulfonate thickener in premium base oils to provide excellent performance in a wide variety of automotive, heavy duty, and industrial applications. It provides dependable performance in a broad range of applications including automotive chassis, wheel bearings, and industrial bearings. It provides excellent corrosion control for high moisture environments.

- QUALITIES:**
- Exceptional Corrosion Protection: CITGO Calsuplex MP Grease provides superior protection against corrosion in the presence of water.
  - Extreme Pressure and Anti-Wear Protection: CITGO Calsuplex MP Grease provides excellent extreme pressure and anti-wear protection under severe conditions.
  - Oxidation Resistance: Calsuplex MP Grease provides outstanding resistance to oxidation.
  - Water Resistance: This product is highly resistant to water washout.

**APPLICATIONS:** CITGO Calsuplex MP Grease is recommended for a wide range of automotive and industrial applications including bearings, ball joints, and bushings. It meets the ASTM D4950 requirements for Wheel Bearing Grease Category GC and Chassis Grease Category LB.

Consult owner’s manual for proper lubricant selection.



**TYPICAL PROPERTIES:**

**CITGO CALSUPLEX MP GREASE**

SAP Code	655582001
NLGI Grade	2
Worked Penetration, ASTM D217	265-295
Thickener Type	Calcium Sulfonate
Color	Green
Texture	Smooth, Adhesive
Dropping Point, ASTM D2265 °F(°C)	500 (260)
Rust Prevention, ASTM D1743	Pass
Water Washout, ASTM D1264, % Loss @ 175°F	2.5
Low Temperature Torque, ASTM D4693, Nm	9.6
High Temperature Life, ASTM D3527, hrs.	120
Four-Ball Wear, ASTM D2266, mm	.05
Four-Ball Weld, ASTM D2596, kgf	400
Four-Ball Load Wear Index, ASTM D2596, kgf	57.7
NLGI Certified, ASTM 4950	GC-LB
ISO Viscosity Grade	150

CITGO, CITGARD and SynDurance are registered trademarks of CITGO Petroleum Corporation. All other registered trademarks or trademarks are the property of their respective owners.

Values shown are typical values only and do not constitute a specification. The information contained herein is subject to change without notice.