# Mystik<sup>®</sup> JT-4<sup>®</sup> Full Synthetic 4-Cycle Marine Engine Oils



#### **OVERVIEW**



- Carefully crafted formulations designed to provide maximum protection under the most demanding marine conditions.
- Specially formulated, proven, and certified for use in 4-cycle marine inboard, outboard, and personal watercraft engines.

# FEATURES & BENEFITS



- Formulated to meet the warranty requirements of Mercury, Yamaha, Evinrude, and other leading OEMs.
- Formulated to meet the demanding requirements of 4-cycle marine engines requiring NMMA FC-W Catalyst Compatible® oils.
- Provide superior rust and corrosion protection in high-performance marine engines under the harshest of marine environments.
- Outstanding scuff and wear protection.
- Ensure maximum engine cleanliness.
- Full synthetic formulations.
- Two viscosity grades for comprehensive category coverage.

### **APPLICATIONS**



- For use in 4-cycle marine inboard, outboard and personal watercraft engines.
- Recommended in applications requiring NMMA FC-W Catalyst Compatible.
- Meet warranty requirements of Mercury, Yamaha, Evinrude and other leading OEMs.
- Mystik JT-4 4-Cycle Full Synthetic 10W-40 provides excellent protection for personal watercraft and meets warranty requirements of Honda, Kawasaki, Polaris, Sea Doo, and other original equipment.
- Refer to equipment owner's manual for proper lubricant recommendation.

NOT FOR USE IN 2-CYCLE OR DIESEL ENGINES.

#### **PROPERTIES**



## Typical Properties for Mystik JT-4 4-Cycle Marine Engine Oils:

Material Code	663094002	663093002
SAE Grade	10W-30 Full Synthetic	10W-40 Full Synthetic
Gravity, ASTM D287, °API	32.0	31.9
Density, lbs/gal	7.21	7.21
Flash Point, ASTM D92, COC °F (°C)	437 (225)	453 (234)
Pour Point, ASTM D97, °F (°C)	-27 (-33)	-22 (-30)
Viscosity, ASTM D445		
cSt at 40°C	80.5	98.4
cSt at 100°C	12.4	14.9
Viscosity Index, ASTM D2270	151	158
CCS Viscosity		
cP at -25°C , ASTM D5293	5900	5660
cP at -10°C , ASTM D5293	_	_
NOACK Volatility, ATM D5800, % Loss	7.2	9
Color, ASTM D1500	2.5	2.5
Sulfated Ash, ASTM D874, m%	1.1	1.1
TBN, ASTM D2896, mg KOH/g	9.3	9.2

Mystik and JT-4 are registered trademarks protected by federal law. All other registered trademarks or trademarks are the property of their respective owners. Values shown are typical values only and do not constitute a specification. The information contained herein is subject to change without notice.